

PHYSICAL PROPERTIES	TEST METHOD	UNIT	0.3 mm	0.5 mm	0.8 mm	1.0 mm
ARTICLE CODE	-	mm	P425B1400003065	P425B1400005040	P425B1400008025	P425B1400010020
WIDTH	-	mm	1400	1400	1400	1400
LENGTH	-	m	65	40	25	20
HAND	-	-	3S	3S	3S	3S
WEIGHT / roll	-	kg	34	35	35	35
WEIGHT / m <sup>2</sup>	-	gr/m <sup>2</sup>	372	620	992	1 240
WEIGHT / m	-	gr /m	520	868	1 390	1 736
FINISH	-	-	SUPER DOUBLE POLISHED			
COLOR	-	-	CRYSTAL CLEAR			
UV STABILIZED	-	-	YES	YES	YES	YES
LOW-TEMPERATURE BRITTLENESS (IMPACT)	ASTM D1790-08	°C	-26	-30	-39	< -40
TEAR RESISTANCE	ASTM D1004-13	N	21.2 (X) 19.8 (Y)	34.2 (X) 32.2 (Y)	58.5 (X) 56.3 (Y)	69.5 (X) 66.7 (Y)
TENSILE STRENGTH	ISO 527-1:2012 ISO 527-3:2001	MPa	25.6 (X) 29.3 (Y)	23.7 (X) 25.3 (Y)	24.2 (X) 27.4 (Y)	20.5 (X) 25.5 (Y)
ELONGATION AT BREAK	ISO 527-1:2012 ISO 527-3:2001	%	350 (X) 320 (Y)	360 (X) 310 (Y)	370 (X) 350 (Y)	380 (X) 420 (Y)
HEAT SHRINKAGE (80°C, 10 min)	DIN 53377:2007	%	0.7 (X) -2.2 (Y)	0.6 (X) -2.9 (Y)	1.0 (X) -2.8 (Y)	0.9 (X) -2.9 (Y)

(X): test proceeded in the width axis  
(Y): test proceeded in the length axis

The data contained in this technical specification is given for information only and is based on our current knowledge of the products concerned.  
This information given to our customer in good faith to inform him and to help him in his search, does not constitute any formal or implicit guarantees as to its use.

